


Red SBR Meter Gaskets - Drop-In & Oval



Red SBR Rubber

Product Code: Style 6105

Description: 75 Duro Red Rubber Sheet **Specifications:** SBR, Styrene-butadiene rubber

Temperature range -30°F to 170°F continuous

Typical Rubber Properties	Test Method	Typical Value
Hardness (Shore A)	ASTM D2240	75 ±5
Tensile Strength	ASTMD412	600 psi min
Elongation	ASTMD412	300% min
Finish	Visual	Plate/Smooth
Color	Visual	Red

Thickness & Width as specified

General Polymer Characteristics:

Styrene-butadiene rubber. A polymer used in the manufacture of expanded rubber. It is very economical and possesses no unique chemical resistance properties. SBR rubber can be compounded to provide very fine abrasion, wear, and tensile qualities. SBR can be readily substituted for natural rubber in many applications with significant cost savings.

Resilience is about the same as natural rubber.